



Slovak Society of Chemical Engineering
Institute of Chemical and Environmental Engineering
Slovak University of Technology in Bratislava

PROCEEDINGS

51st International Conference of the Slovak Society of Chemical Engineering SSCHE 2025

Hotel DRUŽBA
Jasná, Demänovská Dolina, Slovakia
May 27 - 30, 2025

Editors: Assoc. Prof. Mário Mihal'

ISBN: 978-80-8208-158-2, EAN: 9788082081582

Published by the Faculty of Chemical and Food Technology Slovak Technical University in Bratislava in Slovak Chemistry Library for the Institute of Chemical and Environmental Engineering; Radlinského 9, 812 37 Bratislava, 2024

Terada, A., Harada, A., Naoe, K.: Preparation of Ag colloidosomes from Pickering emulsions stabilized by mercaptocarboxylated Ag nanoparticles, Editors: Mihal', M., In *51st International Conference of the Slovak Society of Chemical Engineering SSCHE 2025*, Jasná, Demänovská Dolina, Slovakia, 2025.

Preparation of Ag colloidosomes from Pickering emulsions stabilized by mercaptocarboxylated Ag nanoparticles

Ayumu Terada¹, Ayane Harada¹, Kazumitsu Naoe¹

¹*Dept. of Chemical Engineering, National Institute of Technology, Nara College, Japan,
〒639-1080*

e-mail: am.tyranno@gmail.com

Key words: Ag, nanoparticle, Pickering emulsion, colloidosome

Colloidosomes are hollow superstructures with colloidal particle shells, and they can be prepared by using Pickering emulsion as templates. Specifically, crosslinking/thermal annealing of shell particles, evaporation of inner phases is reported as methods to prepare colloidosomes. Metal colloidosomes are recently developing fields which are potential for anticancer agent [1], photothermal materials [2], etc. Previously, colloidosomes with Fe₃O₄ shells were reported by Yang et al. [3]. It was also reported that Fe₃O₄ colloidosomes have better uptake into tumor cells and show higher stability in tumor cells than their building blocks [1]. However, the preparation of Fe₃O₄ nanoparticles mentioned in the above papers requires extremely high temperature; 300°C and occurs severe reaction during the nanoparticles formation. On the other hand, Ag and Au nanoparticles are also potential for anticancer agent, but Ag nanoparticles which sizes are nearly 10 nm has acute toxicity to mice [4]. In addition, raw materials of Au nanoparticles are very expensive. Therefore, we considered that using Ag nanoparticles (AgNPs) as building blocks can investigate milder and cost-efficient preparation of metal colloidosomes. The aim of this study is to prepare Ag colloidosomes from AgNPs-stabilized Pickering emulsion. First of all, we prepared AgNPs by phase transfer method. The prepared AgNPs were characterized by UV-vis spectroscopy and DLS, which showed its maximum absorption peak was at near 420 nm and their size distribution ranged from 1 to 100 nm, confirming that AgNPs were prepared. Second, we prepared Pickering emulsions using the AgNPs aqueous solution and chloroform as an organic solvent. Fluorescence microscopy measurement of the AgNPs-stabilized Pickering emulsions prepared by adding oil soluble Nile Red to their organic phase confirmed that O/W Pickering emulsion were prepared. Third, we prepared Ag colloidosomes by evaporation of inner phase of the Pickering emulsions by heating at 70°C. The prepared colloidosomes were characterized by DLS, optical microscopy, and SEM with EDS. As a result, ca. 1 μm hollow structures with Ag shells were observed. We observed similarities between the heated Pickering emulsions and creaming-occurred emulsions gained by just leaving them at room temperature for 3 days. Therefore, we successfully prepared colloidosomes with Ag shells by washing the creaming-occurred emulsions, without any heating processes. It was concluded that non-heating preparation of Ag colloidosomes were succeeded, which is milder and more cost-effective than conventional methods.

[1] Nicolas-Boluda, A. et al., *Adv. Funct. Mater.*, 2004274 (2020)

[2] Lopez-de-Luzuriaga, J. et al., *Nanoscale Adv.*, **3**, 198–205 (2021)

[3] Yang, Z. et al., *J. Am. Chem. Soc.*, **138**, 3493–3500 (2016)

[4] Cho, Y. M. et al., *J. Toxic. Pathol.*, **31**, 73–80 (2018)

[5] Cliffler, D. E. et al., *Langmuir*, **16**, 9699–9702 (2000)